

POM | KEPITAL F20-52 LOF | . Grade

- KEPITAL F20-52 LOF . Grade .
- Natural Color Color 가 , UV 가
- .

	ISO 1183	g/cm ³	1.41
	ISO 1133	g/10min	10
(23 , 50 %RH)	ISO 62	%	0.2

(1.8 MPa)	ISO 75		92
	UL 94	-	HB
	ISO 11357		165
	ISO 11359	X 10 ⁻⁵ /	13


	ISO 527	MPa	2600
	ISO 527	MPa	62
	ISO 527	%	10
	ISO 527	%	34
	ISO 178	MPa	83
	ISO 178	MPa	2350
Charpy (Notched, 23)	ISO 179/1eA	kJ/m ²	6.0
Charpy (Notched, -30)	ISO 179/1eA	kJ/m ²	5.5

	IEC 60093	Ω	1x10 ¹⁶
	IEC 60093	Ω • cm	1x10 ¹⁴
	IEC 60243-1	kV/mm	19

(, t = 2 mm)	ISO 294-4	%	2.0
---------------	-----------	---	-----

	ISO 1043	-	POM
--	----------	---	-----

Revision No : 6 (2019-09-17)



1

Tel: 031- 436 -1300

- KOREA POLYACETAL CO., LTD.**