


POM KEPITAL F25-03H		Grade		
- KEPITAL F25-03H		(F20 F30)	Grade .	
- POM		Grade .		
		ISO 1183	g/cm ³	1.41
		ISO 1133	g/10min	13
(23 , 50 %RH)		ISO 62	%	0.2
(1.8 MPa)		ISO 75		101
		UL 94	–	HB
		ISO 11357		170
		ISO 11359	X 10 ⁻⁵ /	12
		ISO 527	MPa	2850
		ISO 527	MPa	68
		ISO 527	%	10
		ISO 527	%	31
		ISO 178	MPa	94
		ISO 178	MPa	2800
Charpy	(Notched, 23)	ISO 179/1eA	kJ/m ²	6.5
Charpy	(Notched, -30)	ISO 179/1eA	kJ/m ²	6.0
		IEC 60093	Ω	1x10 ¹⁶
		IEC 60093	Ω • cm	1x10 ¹⁴
		IEC 60243-1	kV/mm	19
(, t = 2 mm)		ISO 294-4	%	2.0
		ISO 1043	-	POM

Revision No : 3 (2019-09-17)



1

Tel: 031- 436 -1300

- KOREA POLYACETAL CO., LTD.**