


POM KEPITAL TS-25A		Grade		
- KEPITAL TS-25A		Grade		
-		-		
		ISO 1183	g/cm ³	1.39
		ISO 1133	g/10min	15
(23 , 50 %RH)		ISO 62	%	0.2
		ISO 75		90
(1.8 MPa)		UL 94	–	HB
(10 /min)		ISO 11357		165
		ISO 11359	X 10 ⁻⁵ /	13
		ISO 527	MPa	58
		ISO 527	%	12.0
		ISO 527	%	30
		ISO 178	MPa	80
		ISO 178	MPa	2,500
Charpy	(Notched, 23)	ISO 179/1eA	kJ/m ²	6.0
		IEC 60093	Ω	1×10 ¹⁶
		IEC 60093	Ω • cm	1×10 ¹⁴
		IEC 60243-1	kV/mm	-
(, t = 2 mm)		ISO 294-4	%	2.1
		ISO 1043	-	POM

Revision No : 5 (2020-07-21)



1

Tel: 031- 436 -1300

- KOREA POLYACETAL CO., LTD.**