

POM | KEPITAL FT2020 | . Grade

- KEPITAL FT2020 Whisker Grade .

- POM , .

	ISO 1183	g/cm ³	1.59
	ISO 1133	g/10min	15
(23 , 50 %RH)	ISO 62	%	0.23

(1.8 MPa)	ISO 75		152
	UL 94	–	HB
(10 /min)	ISO 11357		165
	ISO 11359	X 10 ⁻⁵ /	6


	ISO 527	MPa	84
	ISO 527	%	-
	ISO 527	%	2.7
	ISO 178	MPa	146
	ISO 178	MPa	6,800
Charpy (Notched, 23)	ISO 179/1eA	kJ/m ²	3.6

	IEC 60093	Ω	1x10 ¹⁶
	IEC 60093	Ω • cm	1x10 ¹⁴
	IEC 60243-1	kV/mm	-

(, t = 2 mm)	ISO 294-4	%	0.9
---------------	-----------	---	-----

	ISO 1043	-	POM-MH20
--	----------	---	----------

Revision No : 4 (2020-07-21)



•

Tel: 031- 436 -1300

- KOREA POLYACETAL CO., LTD.**