


POM KEPITAL TE-24 (FU2020)		Grade	
- KEPITAL TE-24	()	Grade	.
-	Type	Grade	.
	ISO 1183	g/cm ³	1.35
	ISO 1133	g/10min	6
(23 , 50 %RH)	ISO 62	%	0.24
(1.8 MPa)	ISO 75		71
	UL 94	-	HB
(10 /min)	ISO 11357		165
	ISO 11359	X 10 ⁻⁵ /	13
	ISO 527	MPa	41
	ISO 527	%	13.0
	ISO 527	%	> 60
	ISO 178	MPa	53
	ISO 178	MPa	1,450
Charpy (Notched, 23)	ISO 179/1eA	kJ/m ²	18.0
	IEC 60093	Ω	1x10 ¹⁶
	IEC 60093	Ω • cm	1x10 ¹⁴
	IEC 60243-1	kV/mm	21
(, t = 2 mm)	ISO 294-4	%	1.7
	ISO 1043	-	POM-HI

Revision No : 8 (2020-07-21)



1

Tel: 031- 436 -1300

- KOREA POLYACETAL CO., LTD.**